



COVERAGE RATES and WET/DRY MILS

PRODUCT		# GAL PER SQ	WET MIL	DRY MIL
RG-15	No Slope Resurfacing Membrane	5.00	80	44.8
RG-100	Rust Inhibiting Primer	0.40	6.4	2.7
RG-130	Gray Elastomeric Base Coat	1.00	16	8.3
RG-130	Gray Elastomeric Base Coat	1.50	24	12.5
RG-130	Gray Elastomeric Base Coat	2.00	32	16.6
RG-170	White Elastomeric Finish Coat	1.00	16	8.3
RG-170	White Elastomeric Finish Coat	1.50	24	12.5
RG-170	White Elastomeric Finish Coat	2.00	32	16.6
RG-180	Fibered White Elastomeric Finish Coat	1.00	16	8.3
RG-180	Fibered White Elastomeric Finish Coat	1.25	20	10.4
RG-180	Fibered White Elastomeric Finish Coat	1.50	24	12.5
RG-180	Fibered White Elastomeric Finish Coat	2.00	32	16.6
RG-300	BUR/MB Acrylic Primer	1.00	16	8
RG-300	BUR/MB Acrylic Primer	1.50	24	12
RG-400	Universal Bonding Primer	1.00	16	6.4
FW-100A	Air Barrier	2.50	40	20.8

wet film thickness in mils = (#of gal applied per 100 square feet) x 16 mils

dry film thickness in mils = (wet film thickness) x (% volume solids)